


Mesalon™ 7010

Designed for superior strength and chemical compatibility



Mesalon 7010 is a reinforced polymer laminate designed to provide superior chemical resistance, tensile strength and flexibility. 7010 is well suited for 100% aromatic and chlorinated hydrocarbons, alcohols, ETBE, MTBE, Ethanol, Methanol and other chemicals. Mesalon 7010 is designed to provide maximum performance and service life in even the harshest of operating conditions.

	7010-20	7010-35
Base Fabric	Polyester	
Finished Product	Proprietary	
Weight	13.6 oz/yd ²	28 oz/yd ²
FTMS 191-A-5041	461 g/m ²	949 g/m ²
Gauge	.020 in	.035 in
	.51 mm	.89 mm
Standard Width	60 in (1.5 m)	
Tensile Strength Warp	101 lb	101 lb
FTMS 191-A-5100	449 N	449 N
Tensile Strength Fill	103 lb	103 lb
FTMS 191-A-5100	458 N	458 N
Tear Strength Warp	31 lb	32 lb
ASTM D-2261	138 N	142 N
Tear Strength Fill	32 lb	33 lb
ASTM D-2261	142 N	147 N
Temperature Range	-20°F to 200°F -29°C to 93°C	



Values represent nominal average value properties. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.



MLF-7010-08

Northeast
4141 Airport Road
Cincinnati, OH 45226-1643
Phone: 513.321.4511
Fax: 513.321.8178

Southeast
9202 Meadow Vista Blvd.
Houston, TX 77064-2012
Phone: 281.469.8098
Fax: 281.469.9524

West
1726 South Magnolia Ave.
Monrovia, CA 91016-4595
Phone: 626.359.9361
Fax: 626.359.7985