

MesaThane™ 6036AS

Laminated Thermoplastic Urethane (TPU)

Permanent Anti-Static Material with Nondegradeable Properties



MesaThane 6036AS is a reinforced premium-grade urethane laminate featuring superior anti-static properties. 6036AS also offers excellent chemical, abrasion and puncture resistance. It is compatible with 100% aromatic hydrocarbon vapors, gasoline, crude oil and many other chemicals.

	6036-13AS	6036-20AS	6036-25AS	6036-35AS	6036-45AS	6036-55AS
Base Fabric	Polyester					
Finished Product	Urethane					
Weight	9 oz/yd ²	14.1 oz/yd ²	18.3 oz/yd ²	30 oz/yd ²	35 oz/yd ²	45 oz/yd ²
FTMS 191A-5041	305 g/m ²	478 g/m ²	621 g/m ²	1017 g/m ²	1187 g/m ²	1526 g/m ²
Gauge	.013 in	.020 in	.025 in	.035 in	.045 in	.055 in
	.33 mm	.51 mm	.64 mm	.89 mm	1.14 mm	1.40 mm
Standard Width	60 in (1.5 m)					
Tensile Strength Warp	105 lb	101 lb	197 lb	248 lb	253 lb	258 lb
FTMS 191-A-5100	47.63 kg	45.81 kg	89.36 kg	112.49 kg	114.76 kg	117.03 kg
Tensile Strength Fill	100 lb	105 lb	188 lb	255 lb	261 lb	265 lb
FTMS 191-A-5100	45.36 kg	47.63 kg	85.28 kg	115.67 kg	118.39 kg	120.2 kg
Tear Strength Warp	28 lb	30 lb	53 lb	55 lb	57 lb	57lb
ASTM D-2261	12.7 kg	13.61 kg	24.04 kg	24.95 kg	25.85 kg	25.85 kg
Tear Strength Fill	35 lb	33 lb	56 lb	59 lb	60 lb	60 lb
ASTM D-2261	15.88 kg	14.97 kg	25.4 kg	26.76 kg	27.22 kg	27.22 kg
Hydrostatic Resistance	143 psi	150 psi	320 psi	410 psi	450 psi	465 psi
FTMS 191-A-5512	10.1 kg/cm ²	10.6 kg/cm ²	22.5 kg/cm ²	28.8 kg/cm ²	31.6 kg/cm ²	32.7 kg/cm ²
Puncture Resistance	45 lb	60.1 lb	77.3 lb	90 lb	96.3 lb	96.3 lb
ASTM D-4833	20.4 kg	27.26 kg	35.06 kg	40.8 kg	43.68 kg	43.68 kg
Temperature Range	-40°F to 210°F (-40°C to 98.9°C)					
Abrasion Resistance (cycles)	1,500*	2,650*	5,000*	15,000*	45,000*	60,000*
Taber Wheel H-18 / 1kg	*No fabric exposure					
Surface Resistivity	1 x 10 ¹¹ Ohms/Square					
ASTM D-257						

Values represent nominal average value properties. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.



Northeast USA
4141 Airport Road
Cincinnati, OH 45226-1643
Phone: 513.321.4511
Fax: 513.321.8178

Southeast USA
9202 Meadow Vista Blvd.
Houston, TX 77064-2012
Phone: 281.469.8098
Fax: 281.469.9524

West USA
1726 South Magnolia Ave.
Monrovia, CA 91016-4595
Phone: 626.359.9361
Fax: 626.359.7985